

**High Purity.** Total Petrochemicals Polypropylene 3962 features extremely high purity for processing into melt blown micro-fibers.

**Enhanced Productivity.** 3962 produces fine denier melt blown micro-fiber with low process temperatures and die pressures. 3962 exhibits less polymer degradation during processing and improved properties (higher tensile strength, better transport properties, and enhanced basis weight uniformity) in the non-woven web.

**Recommended Applications.** 3962 is recommended for melt blown fiber applications or other applications where low viscosity processing is desired.

**Processing.** 3962 resin processes on conventional extrusion equipment with typical melt temperatures of 500-600°F(260-315°C). Call the nearest Total Petrochemicals Polypropylene Sales Office for additional information.

<u>Resin Properties</u> <sup>(1)</sup>	<u>Typical Value</u>	<u>ASTM Method</u>
Melt Flow, g/10 min.	1300	D-1238 Condition L
Density, g/cc	0.905	D-1505
Melting Point, °F (°C)	330 (165)	DSC <sup>(2)</sup>

**Features:**

- Pelletized Form
- Tertiary butyl alcohol (TBA) free formulation
- Lower Smoke and Odor

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.  
 (2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

Corporate Office USA  
 P.O. Box 674411  
 Houston, TX 77267-4411  
 800.344.3462  
 www.totalpetrochemicalsusa.com

Technical Center  
 P.O. Box 1200  
 Deer Park, TX 77536  
 281.884.7500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or misapplication of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

