TOTAL Polypropylene 4481WZ polypropylene is a nucleated impact copolymer with a Melt Flow of 4.0 g/10min.

TOTAL Polypropylene 4481WZ is characterized by a good stiffness/impact balance coupled with high creep resistance. This grade has been developed for sheet extrusion and thermoforming applications requiring good mechanical properties and aesthetic appearance.

TOTAL Polypropylene 4481WZ has been specially formulated with an additive for excellent antistatic properties as well as good surface appearance and mold release.

Resin Properties	Typical Value	Test Method
Melt Flow, g/10 min.	4.0	ASTM D-1238
Density, g/cm ³	0.905	ASTM D-1505
Melting Range, °C	160 - 165	TOTAL Polypropylene Method
Mechanical Properties		
Tensile Strength at Yield, psi (M Pa)	4900 (34)	ASTM D-638
Elongation at Yield, %	7	ASTM D-638
Flexural Modulus, psi (M Pa)	250,000 (1770)	ASTM D-790
Notched Izod		
@23°C, ft.lb/in.	2.6	ASTM D-256
Thermal Properties		
Heat Deflection Temperature, °C	115	ASTM D-648

4481WZ 8/08

Corporate Office USA P.O. Box 674411 Houston, TX 77267-4411 800.344.3462 www.totalpetrochemicalsusa.com Technical Center P.O. Box 1200 Deer Park, TX 77536 281.884.7500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.



