TOTAL 5720WZ polypropylene is a nucleated impact copolymer with a Melt Flow of 20 g/10min.

TOTAL 5720WZ is characterized by good stiffness, creep resistance, very high impact resistance, excellent antistatic properties and has been formulated to allow faster cycling through early demolding.

TOTAL 5720WZ has been developed specifically for the injection molding of crates, pails, and other heavy duty articles.

Resin Properties	Typical Value	Test Method
Melt Flow, g/10 min.	20	ASTM D-1238
Density, g/cm ³	0.905	ASTM D-1505
Melting Range, °C	160 - 165	TOTAL Method
Mechanical Properties		
Tensile Strength at Yield, psi (M Pa)	3400 (23)	ASTM D-638
Elongation at Yield, %	7	ASTM D-638
Flexural Modulus, psi (M Pa)	190,000 (1,350)	ASTM D-790
Izod Impact (Notched)		
@ 23°C, ft-lb/in (J/m)	3.6 (180)	ASTM D-256
Thermal Properties		
Vicat Softening Point, °C	150	ASTM D-1525
Heat Deflection Temperature, °C	90	ASTM D-648

5720WZ 10/05

Corporate Office USA P.O. Box 674411 Houston, TX 77267-4411 800.344.3462 www.totalpetrochemicalsusa.com Technical Center P.O. Box 1200 Deer Park, TX 77536 281.884.7500

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTYTHAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.



